

1. (Currently amended.) A fire-protection glass product having a heat shielding characteristic, comprising:

a plurality of fireproof glass plates;

a resin intermediate layer interposed between adjacent ones of said glass plates, bonded or adhered to adjacent ones of said glass plates, and made of a material selected from fluorocarbon resin and polyethylene terephthalate resin; and

a heat-ray reflection film ~~formed~~ deposited on the surface of at least one of said glass plates, said heat-ray reflection film being made of a material consisting essentially of a compound selected from the group consisting of indium oxide containing tin, antimony oxide containing tin, tin oxide containing fluorine, and tin oxide containing antimony, and said film having a reflectance of 50% or more, 70% or more, and 80% or more, for light having a wavelength of 1500nm, 2500nm, and 3000nm, respectively, and an average transmittance of 60% or more for visible rays;

~~in combination making a non-intumescent fire-protection product.~~

2. (Original.) A fire-protection glass product as claimed in claim 1, wherein at least one of said fireproof glass plates is made of a heat-resistant transparent crystallized glass.

3. (Cancelled.)

4. (Previously presented.) A fire-protection glass product as claimed in claim 1, wherein said heat-ray reflection film is formed on at least one surface of at least one of said fireproof glass plates.

5. (Cancelled.)

6. (Original.) A fire-protection glass product as claimed in claim 1, wherein said heat-ray reflection film has a thickness between 1000Å and 15000Å.

7. (Cancelled.)

8. (Currently amended.) A fire-protection glass product having a heat shielding characteristic, comprising:

- a plurality of fireproof glass plates;

- a resin intermediate layer interposed between adjacent ones of said glass plates, bonded or adhered to adjacent ones of said glass plates, and made of a material selected from fluorocarbon resin and polyethylene terephthalate resin;

- a heat-ray reflection film formed deposited on the surface of at least one of said glass plates, said heat-ray reflection film being made of a material consisting essentially of a compound selected from the group consisting of indium oxide containing tin, antimony oxide containing tin, tin oxide containing fluorine, and tin oxide containing antimony, and said film having a reflectance of 50% or more, 70% or more, and 80% or more, for light having a wavelength of 1500 nm, 2500 nm, and 3000 nm, respectively, and an average transmittance of 60% or more for visible rays; and

- a double-glazing structure including an additional glass plate attached through an air layer;

~~in combination making a non-intumescent fire-protection product.~~

9. (Currently amended.) A fire-protection glass product having a heat shielding characteristic, comprising:

- two fireproof glass plates;

- a resin intermediate layer interposed between said glass plates, bonded or adhered to adjacent ones of said glass plates, and made of a material of fluorocarbon resin; and

- a heat-ray reflection film formed deposited on the surface of at least one of said glass plates, made of a material consisting essentially of a compound selected from the group consisting of indium oxide containing tin, antimony oxide containing tin, tin oxide containing fluorine, and tin oxide containing antimony, and having a thickness between

1000Å and 15000Å, and having a reflectance of 50% or more for light having a wavelength of 1500nm, a reflectance of 70% or more for light having a wavelength of 2500nm, and a reflectance of 80% or more for light having a wavelength of 3000nm; ~~in combination making a non-intumescent fire-protection product.~~

10. (Previously presented.) A fire-protection glass product as claimed in claim 9, wherein at least one of said fireproof glass plates is made of a heat-resistant transparent crystallized glass.

11. (Previously presented.) The fire-protection glass product of claim 9, wherein said film has an average reflectance of 15% or less for visible rays.

12. (Previously presented.) The fire-protection glass product of claim 10, wherein said film has an average reflectance of 15% or less for visible rays.

13. (Currently amended.) A fire-protection glass product as claimed in claim 8, wherein said plurality includes two glass plates not attached to said additional plate by the air layer, and the heat-ray reflection film is on the outer surface of [[the]] one of said two fireproof glass plates ~~not attached to the additional plate by the air layer..~~